



ARACO TILE FIX PLUS

General Use Cementitious Tile Adhesive

Product Description

ARACO TILE FIX PLUS is a cementitious polymer-modified tile adhesive suitable for fixing a wide range of tiles: Ceramic, porcelain, glass tiles, granite, marble, agglomerated marbles and resin tiles internally and externally on walls, floors.

ARACO TILE FIX PLUS is composed of hydraulic binders, selected aggregates and special additives. It is supplied as a dry powder bag that require the addition of clean water to produce a workable mix.

ARACO TILE FIX PLUS is applied in thickness from 3 mm to 10 mm, depending on the type of tile and the nature of the substrate.

ARACO TILE FIX PLUS meets the requirements for BS FN 12004- 12002 Class C2 F S1.

Uses

ARACO TILE FIX PLUS is suitable to be use:

- For wall and floor applications
- For internal and external application
- For laying tiles over concrete, light weight blocks and cement based screed, mortar and plaster substrate.
- On drywalls such as gypsum, plaster and polystyrene boards (primer use is required).
- For interior and bricks walls

Limitation

It is not recommended to use **ARACO TILE FIX PLUS** in the following cases:

- Rubber, steel and PVC substrate
- Cases that required a rapid utilization for surfaces

Advantages

- Over-heated floors tiling application.
- Tiling over tiles.
- High bond strength.
- High slip resistance.
- High Water and weather resistance
- Chemical resistance



Package: 20 Kg

Consumption: 3 to 7 kg/m2

Surface Preparation

Substrate must be clean and free of all foreign or contaminating materials that might impair the quality of bond such as oils, grease, silt and dust, loose aggregate, sand particles, curing compound. Concrete, hollow blocks and cement based substrates must be sufficient cured and irrigated by water 1 hour prior the application. Surface should appear damp with no water pooling .Gypsum boards, plaster boards, anhydrite screeds must be sufficient dry and free from dust.

Mixing

To prepare the adhesive, pour into a bowl 5L- 6L of clean water. Add the powder to the water and mix them with an electric drill with low rotation speed (300rpm) for 3 minutes until a lump free homogeneous paste is obtained. Allow the mix to stand for 2-3 minutes, then remixed for an additional 1 minute.



Application

Spread the mixed mortar adhesive and firmly pressed onto the surface to be tiled with a notched trowel on an area that can be tiled within 10-15 minutes. Press the tiles firmly to ensure proper bonding with the adhesive .the position of the tile can be adjusted, if required, within 5-10 minutes. Allow the installed tiles to remain undisturbed for at least 48 hours. The tile adhesive must not rise higher in the tile joints not more than half of the tile's thickness. It is recommended to use ARACO GROUT for filling the joints after 2 days of tiles installation

Technical Data

Tensile Adhesion Strength

| | • | |
|-------------------------------|------------|------------|
| In Standard Condition | 1.37 N/mm2 | |
| After water Immersion | 1.04 N/mm2 | |
| After Freeze & Thaw Cycles | 1.08 N/mm2 | BS EN 1346 |
| | | |

Determination of Slip

After Heat Agent

| 0.7 11/ 111112 BG E11 1000 | Average Slip | 0.9 N/mm2 | BS EN 1308 |
|----------------------------|--------------|-----------|------------|
|----------------------------|--------------|-----------|------------|

1.12 N/mm2

Determination of Open time

| Determination of | Open time | |
|------------------|------------|------------|
| At 5 min | 1.29 N/mm2 | |
| At 10 min | 1.25 N/mm2 | BS FN 1346 |
| At 20 min | 1.21 N/mm2 | 20 2 |
| At 30 min | 1.08 N/mm2 | |

Determination of Wetting Capacity

| At 0 min | 100% | |
|-----------|------|------------|
| At 10 min | 97% | BS EN 1347 |
| At 20 min | 55% | |
| Δt 30 min | 25% | |

Transverse Deformation

Average Deformation 2.76 mm BS EN 12002

Product Data

| Appearance | Grey and White Powder |
|-------------------|---|
| Wet Density | 1.5 g/cm3 |
| Pot Life | 1 h @ 25°C |
| VOC | <10 g/ltr |
| Storage condition | Store in a dry area between 5°C and 35°C. Protect from direct sunlight |
| Shelf Life | Original sealed package has a shelf life of 6 months if stored properly |

Safety Instructions

The product may cause skin irritation. Wear gloves and goggles and apply barrier cream to your hands. In contact with eyes or mucous membrane. flush immediately with plenty of warm water and seek medical attention without delay.

Legal Notes

The information, recommendations, and application are based on ARACO current knowledge and experience of the products when properly stored, handled, and applied under normal conditions. ARACO products quaranteed against defective materials and manufacture and sold subject to standard conditions. Users should always refer to the most recent technical data sheet for the product concerned, copies of which will be supplied on request.

More from ARACO

A wide range of construction chemical products is manufactured by ARACO which include:

- Premixed mortar
- Tile adhesives & Grout
- Concrete Repair
- Flooring systems
- Protective Coating
- Waterproofing
- Bonding Agents
- Concrete Admixtures
- Surface Treatments
- Grout & Anchors
- Sealants
- Sports Flooring







Tel: +961 1 562510

Mob: +961 3 104539